

Product data sheet

Address: EXAGON AG
Räffelstrasse 10
8045 Zürich
Phone: 0041 44 430 36 76
Fax: 0041 44 430 36 66
Internet: www.exagon.ch
e-mail: info@exagon.ch



Article description

Modelling clay
Art. 54501 and 54510

Constituents

Binding agent: Synthetic waxes permitted for cosmetics
Filler: Purified natural chalk
Colouring agent: Colour pigments
Other additives: Paraffine oil DAB (pharmaceutical quality)
Glycerol as humectant

Packaging: Block packaging: Cellophane
School box: PP
Cardboard box

PP = polypropylene

Conformity



The Products conform to the European Standard 2009/48/EG 'safety of toys' and therefore bear the CE symbol.

EN71 Tests are in accordance with testing rules contained in European Standard EN 71:
EN71/1 EN71/1 Mechanical and physical properties
EN71/3 EN71/3 Specification for migration of certain elements and
EN71/9 EN71/9 Organic chemical compounds – Requirement.
To be tested: Modelling material and packaging.

ASTM D-4236

Our modelling clay products are tested by ACMI (Art & Creative Material Institute) and conform to the US-Standard ASTM D-4236. According to the standard, a qualified external toxicologist tests the products.

The products meet the Regulations (EG) No. 1907/2006 (REACH) and No. 1272/2008 (CLP) concerning the Registration, Evaluation, Authorization and Restriction of Chemicals.

Labelling clay: The preparation is not classified as hazardous.

Usage notes

For children over 3 years old.

Washable from most of textiles.

Remoldable modelling materials are characterised by permanent deformation.

The heat emitted by the skin and the pressure applied when kneading cause the modelling material to deform. It preserves its form without hardening and can be deformed at any time.